



ROYAL WHITE CEMENT INC.
 White Masonry Cement Specifications
 Type N
 A.S.T.M C-91-05
 Tel: 1-866-655-0000

Physical Requirements	Spec. Limit	Test Result
Fineness, 45 micron: maximum, (% retained):	24	6
Autoclave Expansion, maximum (%)	1.0	0.04
Time of Setting:		
Initial set, (minutes)	120 min	130
	1000 max	265
Compressive strengths, min: MPa (psi)		
7 days	3.4 (500)	8 (1160)
28 days	6.2 (900)	12 (1740)
Air content of mortar: volume (%):		
	8 min	10
	21 max	
Water Retention: (%)	70 min	85

*We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the ASTM C-91-05 specification.