



Quickest Cement

Specification of Quickest Cement

Chemical Analysis

Component		Quickest Cement
SiO ₂		7.68
Al ₂ O ₃		18.60
Fe ₂ O ₃		3.53
CaO		44.80
MgO		0.60
SO ₃		20.66
TiO ₂		0.73
Blaine (m ₂ /kg)		≥600
Compressive Strength (PSI) ASTM C109	1 H	≥ 3550
	3 H	≥ 5500
	1 D	≥ 8000
	28 D	≥10000
Setting time	Initial	15 min
	Final	35 min