

RWC WHITE MASONRY CEMENT


TYPE M, S & N

Product Data Sheet.

**TYPE
M, S & N**

RWC WHITE MASONRY CEMENT is a specialized product, manufactured to exacting standards, it is a white cement base product mainly used for making white or colored mortar.

RWC WHITE MASONRY CEMENT is a low alkali product.



APPLICATIONS

RWC WHITE CEMENT can be used in many constructions Product as follows:

- Brick
- Stone
- Stucco
- Colored mortar
- Colored Masonry
- Low Alkali requirement

QUALITY

RWC WHITE MASONRY CEMENT is produced using the latest technology in Cement Production. It is ground in a special lined Cement Mill with Anhydrite and pure limestone mixed with chemicals to help with flow ability and workability to produce **RWC** a **SUPER WHITE MASONRY CEMENT TYPE M, S & N**.

RWC WHITE MASONRY CEMENT is Super White in Color.

PROPERTIES STRENGTH

Physical Properties

WHITE MASONRY CEMENT	7 Days		28 Days	
Type M	≥ 15mpa	≥ 2175 psi	≥ 20 mpa	≥ 2900 psi
Type S	≥ 13 mpa	≥ 1885 psi	≥ 15 mpa	≥ 2175 psi
Type N	≥ 10 mpa	≥ 1450 psi	≥ 13 mpa	≥ 1885 psi

Other Properties

Fineness 45 Micron	Autoclave Expansion	Initial Set	Final Set	Air Content	Water Retention
≤ 10	≤ 0.1	125 min	265 min	≥ 8	≥ 75

Mix Design

Mix design using **RWC WHITE MASONRY CEMENT** needs to be varied to suit individual application. It is recommended that trial mixes to be carried out prior to commencement of work to ensure that the mix design and material combinations meet the requirements of the specifications of the particular application.

Packaging & Shelf Life

RWC WHITE MASONRY CEMENT is packaged in a specialty bag to protect it from humidity. However, as with all hydraulic Cement / binders, it is recommended that **RWC WHITE MASONRY CEMENT** is not placed outdoors or in direct contact with the ground. When correctly stored in dry conditions, the properties of **RWC WHITE MASONRY CEMENT** will remain within specification limit for at least 6 months. In most cases, its properties will be retained for over a year. **RWC WHITE MASONRY CEMENT** is available in 70 Lb for Type N, and 75 LB for Type M & S it is also available in Super Bag and In Bulk.

ROYAL WHITE CEMENT INC LIMITED WARRANTY

RWC warrants that this product, at the time of shipment, conforms to the Specifications set forth in section 2 of this Product Data Sheet. All other information provided in this Product Data Sheet is for guidance only. ALL OTHER WARRANTIES, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED. RWC sole obligation and the sole and exclusive remedy under this limited warranty shall be the replacement of any nonconforming product, or, at RWC option, the refund of the purchase price. No warranty is given for any technical advice or recommendations provided by RWC. Buyer waives all claims under this limited warranty unless it has given written notice of nonconformity within 30 days of delivery.



ROYAL WHITE CEMENT

8316 EAST FRWY. HOUSTON, TX 77029

1-866-WCEMENT 713-676-0000 (TEL) 713-676-1081 (FAX)

www.royalwhitecement.com