



ROYAL WHITE CEMENT INC.
 White Masonry Cement Specifications
 Type S
 A.S.T.M C-91-05
 Tel: 1-866-655-0000

Physical Requirements	Spec. Limit	Test Result
Fineness, 45 micron: maximum, (% retained):	24	5
Autoclave Expansion, maximum (%)	1.0	0.04
Time of Setting:		
Initial set, (minutes)	90 min	125
	1000 max	265
Compressive strengths, min: MPa (psi)		
7 days	9.0 (1300)	15 (2175)
28 days	14.5 (2100)	21 (3045)
Air content of mortar: volume (%):		
	8 min	12
	19 max	
Water Retention: (%)	70 min	80

*We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the ASTM C-91-05 specification.